

In the Claims:

Please amend the claims as follows:

1-8 (cancelled)

9. (currently amended) A method of making artificial dental bridges, comprising:
prior to carrying out heat treating

applying a suspension comprising particles to densely sintered high strength
ceramic individual bridge parts;

drying the suspension comprising particles to form a layer of particles; and

applying a suspension of glass material to the layer of particles; and

heat treating the individual bridge parts with the applied layer of particles and the
suspension of glass material with a one step heat treatment.

10. (previously presented) The method according to claim 9, wherein the suspension
comprising particles comprises particles, dispersant for the articles, binder for the particles, and a
solvent.

11. (previously presented) The method according to claim 9, wherein the particles
comprise aluminum oxide particles.

12. (previously presented) The method according to claim 9, wherein the suspension of

glass comprises SiO_2 , B_2O_3 , Al_2O_3 , La_2O_3 , and TiO_2 .

13. (previously presented) The method according to claim 9, wherein the individual bridge parts comprise high strength ceramic material with a relative density greater than 98%.

14. (previously presented) The method according to claim 9, wherein the individual bridge parts comprise one or more of the oxides Al_2O_3 , TiO_2 , MgO , ZrO_2 or ZrO_2 with up to 10 mol % Y_2O_3 , MgO or CaO .

15. (previously presented) The method according to claim 9, wherein the suspension of glass has a surface energy at a joining temperature lower than a surface energy for the densely sintered individual bridge parts.

16. (previously presented) The method according to claim 9, wherein the suspension of glass material comprises the same metal oxides as the densely sintered high strength ceramic individual bridge parts in an amount less than a degree of saturation of the metal oxides in the suspension of glass material at the joining temperature.

17. (previously presented) The method according to claim 9, wherein the glass material has a coefficient of thermal expansion that is less than or equal to a coefficient of thermal expansion of the densely sintered high strength ceramic individual bridge parts.

18. (previously presented) The method according to claim 9, wherein the glass material

comprises SiO_2 32 mol %, B_2O_3 24 mol %, Al_2O_3 18 mol %, and La_2O_3 12 mol %.

19. (previously presented) The method according to claim 9, wherein the particles in the layer of particles are large enough such that drying stresses on removal of solvent from the suspension of glass material do not lead to catastrophic failure of the dental bridge prior to melting and solidification of the glass material.